



01/24/2024

3-3x1.5

Procedure	Sieve/Test	Average	Unit	3 x 1.5
	4" (100mm)	100.0	%	100-100
	3 1/2" (90mm)	94.7	%	90-100
	3" (75mm)	78.0	%	
	2 1/2" (63mm)	55.8	%	25-60
	1 1/2" (37.5mm)	10.0	%	0-15
	3/4" (19mm)	2.3	%	0-5

Name/Title Christopher Covey / Materials Performance
Technician